



136 Coonbrook Road • P.O. Box 69  
Petersburgh, New York 12138  
Telephone: 518.658.3202  
Fax: 518.658.3204

---

<b>Product Code</b>	<b>8195</b>	
Substrate Type	1/16" open mesh	
Coating Medium	Polytetrafluoroethylene	
Coated Weight	0.890 – 1.010 483 – 548	(pounds/yd <sup>2</sup> .) (grams/m <sup>2</sup> )
Overall Thickness	0.020" - 0.023" 0.508 – 0.584	(inches) (mm)
Substrate Thickness (nominal)	0.165" 0.419	(inches) (mm)
Operating Temperature	-100°F to +400°F -73°C to +204°C	(continuous)
Breaking Strength (minimum)	w= 300 / f=300 2627 / 2627	(pounds/inch of width) (Newtons/5cm)
Window Opening Size (nominal)	0.062" 1.57	(inches) (mm)

---

The data herein is based on controlled sample test results. The information is intended for comparison purposes only as each manufactured lot will exhibit normal variation. Users are expected to determine product suitability for their specific intended use before application. All data is subject to change without notice.