



Product Specification 7208

Taconic 7208 is a standard 20 mil PTFE coated fiberglass fabric. This material exhibits release properties, heat resistance, and chemical resistance. This material is designed to be a strong fabric with high tear strength and structurally sound to prevent distortion. Common applications include tray lining, wear stripping, and gaskets and seals. Maximum width is 140" wide.

Product Properties	Units	Value	Tolerance	Test Method
Reinforcing Substrate		E-GLASS		
Coating Type		PTFE		
% Coating	%	51	+/- 2%	
Total Coated Weight	lbs/yd2	1.52	+/- 5%	ASTM D4969
Nominal Thickness	inch	0.02		ASTM D4969
Coating Adhesion Strength	lbs/in	9.5	Typical	ASTM D751
		6.5	Minimum	
Dielectric Breakdown	volts/mil	240	Typical	ASTM D149 Method A
		155	Minimum	
Tensile Strength	lbf/in	375	Typical Warp	ASTM D902
		240	Minimum Warp	
		355	Typical Fill	
		220	Minimum Fill	
Tear Strength	lbs	17	Typical Warp	ASTM D5587
		9	Minimum Warp	
		15	Typical Fill	
		7	Minimum Fill	
Operating Temperature	°Fahrenheit	-100° to +500°		

Information contained in this document is based on our general experience and is given in good faith, but we are unable to accept responsibility in respect to factors which are outside our knowledge or control. All data is subject to change without notice.

This product is suitable for direct and repeated use in a food contact application when used in accordance with the product specifications.



Please contact us for samples or a quotation

Taconic Headquarters
Petersburgh, NY
www.4taconic.com
info@4taconic.com

Western US, Mexico & Central America
La Verne, CA
www.4taconic.com
info@4taconic.com

Canada
Mississauga, CAN
www.4taconic.com
info@4taconic.com



For queries in Europe please visit www.taconic-ipd.com
or email info@taconic-ipd.com

