



## Product Specification 7278

Taconic 7278 is a standard 27 mil PTFE coated fiberglass fabric. This material exhibits release properties, heat resistance, and chemical resistance. This material is designed to be a strong fabric with high tear strength and structurally sound to prevent distortion. Common applications include tray lining, wear stripping, and gaskets and seals. The fabric is often used in presses for automotive applications. Maximum width is 181" wide.

Product Properties	Units	Value	Tolerance	Test Method
Reinforcing Substrate		E-GLASS		
Coating Type		PTFE		
% Coating	%	39	+/- 2%	
Total Coated Weight	lbs/yd2	1.83	+/- 5%	ASTM D4969
Nominal Thickness	inch	0.0255		ASTM D4969
Coating Adhesion Strength	lbs/in	9.5	Typical	- ASTM D751
		7	Minimum	
Dielectric Breakdown	volts/mil	170	Typical	ASTM D149 Method A
		100	Minimum	
Tensile Strength	lbf/in -	400	Typical Warp	ASTM D902
		300	Minimum Warp	
		500	Typical Fill	
		400	Minimum Fill	
Tear Strength	lbs -	25	Typical Warp	- ASTM D5587
		15	Minimum Warp	
		20	Typical Fill	
		8	Minimum Fill	
Operating Temperature	°Fahrenheit	-100° to +500°		

Information contained in this document is based on our general experience and is given in good faith, but we are unable to accept responsibility in respect to factors which are outside our knowledge or control. All data is subject to change without notice.

This product is suitable for direct and repeated use in a food contact application when used in accordance with the product specifications.



info@4taconic.com





Please contact us for samples or a quotation

Western US, Mexico & Central America

La Verne, CA

www.4taconic.com info@4taconic.com

For queries in Europe please visit <a href="www.taconic-ipd.com">www.taconic-ipd.com</a> or email <a href="mailto:info@taconic-ipd.com">info@taconic-ipd.com</a>

Canada Mississauga, CAN www.4taconic.com info@4taconic.com





Rev: 01/25 - 004