



Product Specification

7025-60/80-CFM

Taconic 7025 60/80 is a 2 mil porous PTFE coated fiberglass fabric with a porosity range of 50-90 CFMs. This material is referred to as a bleeder cloth. This fabric is commonly used as a release sheet in the production of composite materials. The construction of the fabric allows for release properties and "bleed through" where required. Maximum width is 61.5" wide.

Product Properties	Units	Value	Tolerance	Test Method
Reinforcing Substrate		E-GLASS		
Coating Type		PTFE		
% Coating	%	29	+/- 2%	
Total Coated Weight	lbs/yd2	0.12	+/- 5%	ASTM D4969
Nominal Thickness	inch	0.0025		ASTM D4969
Tensile Strength	lbf/in	55	Typical Warp	- ASTM D902
		45	Minimum Warp	
		50	Typical Fill	
		40	Minimum Fill	
Tear Strength	lbs	4.5	Typical Warp	- ASTM D5587
		3.5	Minimum Warp	
		6	Typical Fill	
		5	Minimum Fill	
Porosity	CFM	50	Nominal	ASTM D737
Operating Temperature	°Fahrenheit	-100° to +500°		

Information contained in this document is based on our general experience and is given in good faith, but we are unable to accept responsibility in respect to factors which are outside our knowledge or control. All data is subject to change without notice.



The state of the s

Please contact us for samples or a quotation

Western US, Mexico & Central America La Verne, CA

www.4taconic.com info@4taconic.com

For queries in Europe please visit www.taconic-ipd.com or email info@taconic-ipd.com

Canada Mississauga, CAN www.4taconic.com info@4taconic.com





Rev: 04/24 - 005