

Typical Properties

Substrate Type	Leno Weave Kevlar®	
Coating Medium	Pigmented Polytetrafluoroethylene	
Coated Weight (nominal)	0.540 292.9	(pounds/sq.yard) (grams/sq.meter)
Overall Thickness (nominal)	0.025 0.6350	(inches) (mm)
Operating Temperature	-100°F to 356°F -73°C to 180°C	(continuous)
Tensile Strength (warp/fill) (nominal)	275 / N/A 2408 / N/A	(pounds/inch of width) (mm)
Window Opening Size (nominal)	0.167 X 0.167 4.2418 X 4.2418	(inches) (mm)
Opening Area (average)	0.0278 17.931	(inches/2) (mm/2)

The data herein is based on the authoritative testing of several lot numbers. This information is intended for comparison purposes only, each lot number will vary from the published data.



136 Coonbrook Road • P.O. Box 69
Petersburgh, New York 12138
Telephone: (800) 833-1805 / (518) 658-3202
Fax: (518) 658-3186 www.4taconic.com

