



## Product Specification

**6625-11**

Taconic 6625-11 is a 11 mil aluminium foil flame spray tape with glass reinforcement and a high temperature silicone adhesive. This tape is designed for precision masking of components during flame spray and plasma spray coating applications and leaves little-to-no residue upon removal. The foil allows for precision coating lines and true edges. 6625-11 is self-wound with no release liner. Maximum width is 34" wide

Product Properties	Units	Value	Test Method
Adhesive Type		<b>Silicone</b>	
Substrate Type		<b>E-glass and Aluminium Foil</b>	
Total Weight of Composite	lbs/yd <sup>2</sup>	0.825	ASTM D4969
Adhesive Thickness	inches	0.0043	ASTM D3652
Substrate Thickness	inches	0.0062	ASTM D3652
Total Product Thickness	inches	0.0105	ASTM D3652
Adhesive Strength	oz/in-width	50 Typical	ASTM D3330 Method A
		35 Minimum	
Adhesive Shelf Life	Months	12	From DOM
Operating Temperature	°Fahrenheit	-100° to +500°	

Storage conditions for all Tapes: Temperature-23 C +/- 4 C (66.2F~80.6F) and Relative Humidity- 50% +/- 10%

Information contained in this document is based on our general experience and is given in good faith, but we are unable to accept responsibility in respect to factors which are outside our knowledge or control. All data is subject to change without notice.



#3083

**Taconic Headquarters**  
Petersburgh, NY  
[www.4taconic.com](http://www.4taconic.com)  
[info@4taconic.com](mailto:info@4taconic.com)

Please contact us for samples or a quotation

**Western US, Mexico & Central America**  
La Verne, CA  
[www.4taconic.com](http://www.4taconic.com)  
[info@4taconic.com](mailto:info@4taconic.com)

**Canada**  
Mississauga, CAN  
[www.4taconic.com](http://www.4taconic.com)  
[info@4taconic.com](mailto:info@4taconic.com)



For queries in Europe please visit [www.taconic-ipd.com](http://www.taconic-ipd.com) or email [info@taconic-ipd.com](mailto:info@taconic-ipd.com)

