

Description

A2023 A/B is a two-component addition cured RTV silicone rubber with putty-like consistency and a short cure period.

Typical Properties

One/Two Component	Two
Mix Ratio by Weight	1:1
Pot Life	2 min
Curing Time	6 min
A Color, B Color	White, Blue
Shore A Hardness	40
Tensile	550 psi
Elongation	225%
Density at 23C	1.40 g/cm ³
Storage Stability at RT	12 months

Test method

ASTM D2240
ASTM D412
ASTM D412
ASTM D297

Specification Writers: These values are not intended for use in preparing specifications.

How to Use

Mix equal parts A and B, then press against master or part to create a mold or masking area. The rubber exhibits a short cure period of 6 minutes. For specific information regarding safe handling of this material, please refer to the Safety Data Sheet.

Limited Warranty Information – Please read Carefully

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of Taconic's products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Taconic's products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent. Taconic's sole warranty is that our products will meet the sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. **TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, TACONIC SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. TACONIC DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**



136 Coonbrook Road • P.O. Box 69
Petersburgh, New York 12138
Telephone: (800) 833-1805 / (518) 658-3202
Fax: (518) 658-3186 www.4taconic.com

